

# SI3104

## Stretchable Printed Insulator

### Product Description

ACI SI3104 is a screen printable, thermally cured ink that is stretchable when cured and compatible with ACI's stretchable inks. SI3104 can be used as an insulator and/ or crossover dielectric. When cured, the ink displays exceptional durability, excellent flexibility, and high insulation resistance. SI3104 has excellent adhesion to TPU, and is fully compatible with ACI's suite of products engineered for stretchable and flexible electronics.

### Product Benefits

- Excellent adhesion to elastomeric substrates
- Maintains flexibility and stretchability to more than 100% elongation
- Good dielectric breakdown strength
- Fully compatible with ACI's stretchable inks and conductive adhesives

Typical Performance			
DC Breakdown <sup>1</sup>	250 V/mil		
Adhesion <sup>2</sup>	5B		
Maximum Elongation	100%		
<sup>1</sup> Three layers printed with 180.0018 Stainless Steel mesh (ACI DC Voltage Breakdown Test)			
<sup>2</sup> Method based on ASTM D3359 Method B tested on 0.005" Melinex® ST506 PET			
Typical Properties as Supplied			
Physical State	Paste/Ink		
Color	Translucent White		
Viscosity <sup>3</sup>	33 Pa·s		
Density	1.15 g/mL		
Percent Solids <sup>4</sup>	32%		
Shelf Life at 20°C	12 Months		
Typical Processing Parameters			
Deposition methods	Screen printing		
Ideal Curing Time and Temperatures	5-15 min in box oven at 135°C 5 min in industrial conveyor oven at 135°C		
Recommended Screen Mesh Range TPI/Wire Diameter	150/0.0026" – 200/0.0016" Stainless Steel 110/43µm – 140/55µm PET		
Emulsion Over Mesh (EOM) Thickness	15 µm		
Squeegee Durometer	70A – 80A		
Recommended Meshes - Theoretical Dry Film Thickness - Coverage	150/0.0026"	14 µm DFT	12 m2/kg
	200/0.0016"	9 µm DFT	15 m2/kg
Recommended # Layers	110/43µm	14 µm	12 m2/kg
	140/55µm	10 µm	15 m2/kg
Recommended # Layers	3		
Mixing	Slow thorough mix, avoid inducing bubbles, fixed spatula in rotating jar ideal <sup>5</sup>		
Thinner/Diluent	SE8106		
Storage	In sealed container in cool dry location		
Clean Up Solvents	Acetone, MEK, and similar solvents		
<sup>3</sup> Measured on Anton Paar MCR302 at 10 <sup>-1</sup> sec shear rate at 25°C after pre-shearing at 100 <sup>-1</sup> sec for 5 min			
<sup>4</sup> 150 °C for 120 minutes in box oven			
<sup>5</sup> AT-LM4 Stirring Type Mixer (E211) recommended			

## Contact ACI

Email: [info@acimaterials.com](mailto:info@acimaterials.com)

Phone: 805-324-4486

Website: [www.acimaterials.com](http://www.acimaterials.com)

## Mailing and Shipment Address

ACI Materials, Inc.

44 Castilian Drive

Goleta, CA 93117

## Caution

Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapors emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

## Disclaimer

The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. Applied Cavitation, Inc. assumes no liability for any injury, loss, or damage, direct or consequential arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make their own tests to determine the suitability thereof for their particular use, before using it. User assumes all risk and liability whatsoever in connection with their intended use. Applied Cavitation's only obligation shall be to replace such quantity of the product proved defective.

